EUROPEAN PATENT APPLICATION

(72) Inventor: Borggreve, Reinoldus Jozef Maria
Frank Smitsstraat 1
NL-6336 VG Hulsberg (NL)
Inventor: de Brabander-van den Berg, Ellen
Marleen Monique
Provinciale Weg Zuid 30
NL-6438 BE Schinnen (NL)
Inventor: Beusen, Guido Petrus Cornelus
Roosevelthof 15
NL-6333 EL Nuth (NL)

(54) **Preparation of star-branched polymers.**

(57) The invention relates to a process for the preparation of star-branched polymers by reaction in the melt of a polymer having at least one hetero atom in the chain with a compound having at least three functional groups. Suitable polymers are for instance polyamides, polyesters, polyurethanes, polyoxyalkyls, polyimines and copolymers of these. Functional groups are for instance amine, carboxyl, hydroxyl, isocyanate and imine groups.

The process is very fast and requires no special purification.

The process enables star-branched polymers to be prepared which are derived from so-called AABB polycondensates.

EP 0 672 703 A1

The invention relates to a process for the preparation of star-branched polymers. Various such polymers, consisting of an at least tri-functional core molecule from which emanate linear polymer chains, are described in the literature, but they have hardly found any technical application owing to the complicated methods of preparation that have been developed so far. In the known methods of preparation the monomer for the polymer chains is started from and the polymerization is initiated by the multifunctional core molecule. Examples of this are described in K.R. Gorda and D.C. Pfeifer, J. Appl. Polym. Sc. 50, 1977-83 (1993) and J.M. Warakomski, Chem. Mater. 4, 1000-04 (1992).

The first-mentioned publication describes the preparation of star-branched polymer on the basis of (di-)pentaerythritol as core molecule and initiator for the ring-opening polymerization of ε-caprolactone to poly(ε-caprolactone) chains. This polymerization is carried out in the presence of stannous octate as catalyst. Nevertheless it takes at least 12 hours to achieve complete conversion of the caprolactone. Dimethylformamide is used as solvent, from which the star-branched polymer is recovered through precipitation in diethyl ether. In order to remove the dimethylformamide out of the product, repeated washing with large quantities of diethyl ether is required.

The second publication describes the preparation of a star-branched polymer on the basis of various polyethylene imines as core molecule and initiator for the ring-opening polymerization of ε-caprolactam to poly(ε-caprolactam). This publication also mentions two other methods, starting from a core molecule with several carboxy acid sites at which the poly(ε-caprolactam) chains are formed through hydrolytic ring-opening polymerization, respectively from tris caprolactam as core molecule at which the star-branched polymer is formed through anionic polymerization of caprolactam.

The drawback of all these methods is that they take much time and require the use of very pure raw materials in order to prevent unwanted polymerization initiation. For instance, monomers and solvents have to be water free to a high extent. Also, an extensive purification step is required for the removal of residues of monomer and oligomer and/or solvent. A further restriction of the known processes is that they can only be used for polymers based on so-called head-to-tail monomer bonds and in the formation of which no low-molecular compounds such as water, methanol and ammonia are produced, which are products usually formed in polycondensation reactions.

The object of the invention is to provide a process for the preparation of star-branched polymers which does not have said drawbacks and is suitable for application on a commercial scale.

The inventors have succeeded in developing a process which is widely applicable and yields star-branched polymers in surprisingly short production times.

The process according to the invention is characterized by reaction in the melt of a polymer having at least one hetero atom in the chain with a compound having at least three functional groups.

Very surprisingly it has been found that full conversion to star-branched polymer takes place when a mixture of poly(ε-caprolactam), also called nylon-6, and 1,4-diaminobutane-N,N'-tetra-1-propylamine is extruded at 270°C with a retention time of 3 minutes. Without any further purification the star-branched polymer thus obtained can be used for the manufacture of moulded articles, film or fibres.

The molecular weight of the star-branched polymer obtained can be varied by selecting the molecular weight of the polymer started from and/or the polymer : core molecule ratio. With an n-functional compound the molar ratio, on the basis of number average molecular weight, between the initial polymer and the compound will generally be chosen lower than the value n. The molar ratio preferably is less than 1/2n.

In the case of a ratio ≤ 0.1n the mechanical properties of the star-branched polymer obtained are insufficient in general. By preference a ratio higher than 0.2n is chosen.

Optionally, the process according to the invention can be carried out in the presence of a catalyst. Suitable catalysts are for instance metal oxides, for instance antimony oxide, borates, acids, metal alkyls, for instance tetrabutyl titanate, phosphorus compounds, for instance triphenyl phosphite, phosphates and phosphonates.

Suitable polymers are polymers having at least one hetero atom in the chain. Examples of such polymers are polyamides, polyurethanes, polyesters, polyoxyalkylenes, polyimines and copolymers of these. Preferably, these polymers are only slightly branched or not at all.

The polyamides may have been obtained by polycondensation of di-acids and diamines or α,ω-amino acids, as well as by ring-opening addition of a lactam. Particularly suitable are polyamides derived from α,ω-aminoacids and the corresponding lactams, for instance nylon-4, nylon-6, nylon-8, nylon-11 and nylon-12.

The polyesters may have been obtained by polycondensation of diols and di-acids or α,ω-hydroxy acids as well as by ring-opening polymerization of lactones. The group of polyesters is understood to include polysulphones and polycarbonates. Particularly suitable are polyesters obtained by ring-opening polymerization and polyesters derived from α,ω-hydroxy acids, for instance polylactones.

A suitable polyoxyalkylene is for instance polyoxyethylene, which, in the presence of cationic groups, which preferably are already present in the core molecule, brings about rapid conversion to star-branched polyoxyethylenes.

5   In principle all molecules having at least three functional groups can be used as core molecule, a functional group being understood to be a reactive group capable of reacting with a chain fragment which is released when fracture occurs at the hetero atom in the polymer comprising a hetero atom, in which reaction the chain fragment is coupled to the core molecule. The chain fracture is preferably initiated by the functional group of the core molecule. The functional groups of the core molecule can be chosen in dependence on the polymer with the hetero atom in the chain.

10   Suitable functional groups in general are hydroxyl or thiol, (carboxy) acid, epoxide, acid anhydride, acid chloride, nitrile, isocyanate, imine and amine groups, which are optionally substituted, and precursors thereof in so far as not already mentioned in the foregoing.

    In the case of polyamides, high-boiling tris or higher functional amines or imines, for instance lysine, are used by preference. Special preference is given to dendrimer molecules, which bring about a spherical structure with little chain linkage. Highly suitable in this case are dendrimer amines of the formula:

15

20

25

30 where R_1-R_8 = -H,-$(CH_2)_3$-NH_2, -$(CH_2)_3$-$N[(CH_2)_3$-$NH_2]_2$, etc. and p = 1, 2, 3 etc. Preferable p is 6 at most.

According to the proposal for nomenclature in J.Pol.Sci., Part A, 31, 641-51 (1993) by G. Newkome et al. these are, in case p = 3,

4-cascade : 1,4-diaminobutane[4] : propylamine

35 8-cascade : 1,4-diaminobutane[4] : (1-azobutylidene)^4: propylamine

16-cascade : 1,4-diaminobutane[4] : (1-azobutylidene)^{12}: propylamine

respectively, etc. dendrimers,

These show very high reactivity and bring about full conversion of linear polyamide 6 to a star-branched polyamide within 3 minutes.

40 The precursor of this compound, comprising a nitrile group instead of -CH-NH$_2$, can also be used; (4-cascade : 1,4-diaminobutane[4] : propionitrile etc.).

    Besides the amines mentioned above, core molecules having 3 or more hydroxyl groups, for instance pentaerythritol and dipentaerythritol, as well as core molecules having 3 or more acid terminal groups, are also very suitable for the preparation of star-branched polyesters.

45   The process according to the invention is particularly suitable for polymers that have a high melting point. The melting point preferably is higher than 160°C, more preferably higher than 180°C. It is particularly advantageous if the melting point is higher than 200°C, in particular higher than 220°C.

    The molecular weight of the polymer with a hetero atom in the chain may vary within wide limits. For instance, the number average molecular weight may vary between 10,000 and 100,000. If the molecular 50 weight is low, the polymer : compound ratio is preferably chosen higher, for instance between 1 and n. If the molecular weight is high, said ratio may be chosen lower, without causing the mechanical properties of the resulting star-branched polymer to be inferior to those of the starting polymer for the chains.

    Star-branched polymers are distinguished by the following properties from the corresponding non-branched polymers having a corresponding number average molecular weight.

55   1. The viscosity of the melt is many times lower than that of the non-branched polymer having a corresponding total molecular weight. Warakomski reports a value higher than 6 for the ratio between the melt viscosity of linear polyamide 6 and that of star-branched polyamide 6 at 220-250°C. The ratio between the intrinsic viscosities, however, is less than 2. This is attributed to the smaller giral diameter of

3

the star-branched polymers.

2. The mechanical properties are comparable, although the elongation at break as well as the impact resistance are smaller for the star-branched polymer. This is to be attributed to the fact that in the star-branched polymers the length of the chains is smaller, while moreover the star-shaped structure makes interaction between the chains more difficult. If the chain lengths are becoming too short, which is for instance the case if the total molecular weight is too low or if the degree of branching is too high, the mechanical properties show a clear decline.

The process according to the invention can in principle be put into practice on all current types of melt mixing apparatus. Particularly suitable are twinscrew extruders in which very intensive mixing is accomplished.

The invention will now be elucidated by means of the following non-restrictive examples.

The following test methods were used for the characterization of the polymers.

- Notched impact resistance: ASTM D256, 23·C kJ/m^2
- Elongation strain test: ASTM 638, 23·C
  yield stress N/mm^2
  drawing stress N/mm^2
  fracture stress N/mm^2
  elongation at break %
- Three-point bending test: ASTM D790, 23·C E-modulus N/mm^2
  max. flexural load N/mm^2
- Dynamic Mechanical Analysis: Rheometrics 800 plate/plate, 240·C, measured from high to low frequency.
  η_0 (melt viscosity) Pa.s
- Differential Scanning Calorimetry: scanning rate 10·C/min up to 230·C; heat of fusion (2nd heating curve) J/g
- Intrinsic viscosimetry: 25·C in 90% formic acid (0.5 g/100 ml) ISO 307. Viscosity number, VGm and η_{rel}.
- Molecular weight determination (Mw): by means of gel permeation chromatography (GPC) with hexafluoroisopropanol as solvent and by means of light scattering measurement om 2 mol KCl in 0.5% formic acid, dissolution time 3 hours, and after filtration through a 0.5 mμ filter.
- Determination of terminal groups: titrimetric, mgeq/g.

Example I

Nylon-6 powder is pre-mixed with 0 to 5 wt.% 4 cascade: 1,4-diaminobutane[4] : propylamine, (DAB-(PA)$_4$), obtained by adding acrylonitrile to 1,4-diaminobutane through Michael's addition, followed by hydrogenation of the terminal nitrile groups, and melt-mixed on a Berstorff ZSE 25 twin-screw extruder (L/D = 33) under the following conditions: cylinder temperature 200-300·C, 300 rpm; throughput: 2 kg/h under nitrogen in the hopper. Retention time about 3 minutes. On an Arburg injection-moulding machine the granulate is injection-moulded to test bars at a temperature setting of 240-260·C, a mould temperature of 80·C and a cycle time of about 47 seconds. The test bars were used for notched impact resistance and tensile strength tests. The melt viscosity, intrinsic viscosity and molecular weight were determined on the granulate by means of light scattering and gel permeation chromatography.

The characterization results for the various compositions are presented in Table 1:

Nylon-6	100	99.975	99.95	99.5	99.0	98.0	95.0
DAB(PA)$_4$	0	0.025	0.05	0.5	1.0	2.0	5.0
IZOD	6.1	5.9	5.7	6.0	6.1	5.6	5.6
yield stress	78	78	77	79	80	77	66
elongation at break	63	48	41	35	41	34	36
E-modulus	3000			2980	2980	2980	2650
melt viscosity η_0	3.42			2.70	2.52	2.48	2.27
intrinsic viscosity	2700	2199	1559	560	390	300	170
heat of fusion	71.3			74.0	74.2	78.5	79.5

From this table it appears that with increasing DAB(PA)$_4$ content the melt viscosity of the nylon-6 decreases. The intrinsic viscosity also decreases.

The terminal group determination on the composition containing 1 wt.% DAB(PA)$_4$ shows the following results. The titrimetric terminal group analysis was performed after extraction of the granulate with methanol.

	terminal group [meq/g]		
	NH$_2$	COOH	Mw
nylon-6[1])	0.036	0.035	53,000
DAB(PA)$_4$ (1%)	0.127 (calculated)		
nylon-6 + 1 wt.% DAB(PA)$_4$	0.12	0.006	49,000

[1]AKULON F 135C from DSM, Netherlands, Mn = 27000, Mw = 53000

Extract 1.6 wt.%, linear nylon fragments (<10,000). With NMR no DAB(PA)$_4$ is found in the extract; apparently all DAB(PA)$_4$ has reacted.

The above results indicate that all DAB(PA)$_4$ is bound to the nylon. It also appears that the difference between the NH$_2$ and COOH terminal groups has remained virtually constant. The acid terminal groups have reacted virtually completely with free amine terminal groups of the DAB(PA)$_4$. If there had only been reaction with the COOH terminal groups, then on average approximately one amine group would have reacted per DAB(PA)$_4$ molecule. The molecular weight and the properties of the nylon would show no significant change in that case.

However, a very strong decrease of the melt viscosity occurs, from 2700 to 390 Pa.s, which is characteristic of the formation of a star-branched nylon. These phenomena could be attributed to the following mechanism.

However the invention is not bound to any theoretical explanation.

In the melt, under the influence of the amine groups of the DAB(PA)$_4$ or otherwise, chain rupture occurs at amide groups in the polyamide chain. The fragment containing the carboxy groups reacts with an amine terminal group of the DAB(PA)$_4$, while the other chain fragment is amineterminated. This takes place in accordance with the following reaction scheme:

$$R_1-N^H-\underset{\underset{O}{\|}}{C}-R_2 + -(CH_2)_3-NH_2 \rightarrow R_1-NH_2 + -(CH_2)_3-N^H-\underset{\underset{O}{\|}}{C}-R_2$$

This reaction repeats until all free amine groups of the DAB(PA)$_4$ are occupied. In the case of DAB(PA)$_4$ a star-branched nylon will be formed in this way, with the nylon branches having an average length of about 1/4 of those of the original nylon. Since rupture can occur at any place in the chain, there will be a wide spread in the lengths of the nylon chains of the star-branched polymer, by which it is distinguished from the

star-branched nylons prepared according to the state of the art by controlled chain growth on the core molecule, which would show a relatively narrow molecular weight distribution.

From the variation of the mechanical properties it appears that if 5 wt.% DAB(PA)₄ is used, i.e. that if the length of the nylon chain in the branches becomes on average 15 to 20 times shorter than in the starting polymer, the mechanical properties decline, which is in agreement with the expectations regarding a star-branched polymer. The melt viscosity is very low then: about 15 times lower than that of the starting nylon.

Example II

Example I is repeated, but instead of nylon-6, nylon-6,6*)is used now. Also in this case a decrease in melt viscosity is observed, as manifested for instance in an almost fivefold decrease in the die pressure of the extruder. The mechanical properties show a decline if the DAB(PA)₄ concentration $\geq$ 2 wt.%. This is to be expected since the molecular weight of the starting nylon is less high than that of the nylon 6 of example I.

Example III

Polybutylene terephthalate*with 0.35 wt.% DAB(PA)₄ was extruded to granulate on a Werner and Pfleiderer ZSK 30 extruder with a cylinder temperature setting of 250°C, a speed of 225 rpm and a throughput of 14 kg/h. The melt viscosity again shows a strong decrease, in the presence of the 4-functional molecule.

Aftercondensation of the low-viscous material obtained to a relative viscosity higher than the non-modified material does not result in a higher melt viscosity than that of the initial product.

Example IV

Example II is repeated, but now using polyethylene terephthalate**, with a cylinder temperature setting of 270°C. Again the considerable melt viscosity decrease characteristic of star-branched polymers occurs. The mechanical properties of the branched polyester are of the same level as those of the linear starting polymer.

By means of the foregoing examples it has been shown that with application of the process according to the invention it is not only possible to prepare star-branched polymers with an AB polyamide or polyester in the chains, but also star-branched polymers with AABB-type polyamides and polyesters obtained via polycondensates of di-acids and diamines or diols, respectively, which is not possible with the techniques according to the state of the art.

To the average person skilled in the art it will be clear from the above examples that by choosing a different core compound and/or different polymers, a wide variety of star-branched polymers can be obtained, the choice of the polymer being determined by the possibility of chain rupture at the site of a hetero atom in the chain.

Claims

1. Process for the preparation of a star-branched polymer by reaction in the melt of a polymer having a hetero atom in the chain with a compound having at least three functional groups.

2. Process according to claim 1, characterized in that the polymer having a hetero atom in the chain is chosen from the group comprising polyamides, polyesters, polyurethanes, polyoxy alkylenes, polyimines and copolymers of these.

*) Mn = 18,000, Mw = 33,000

* PBT, rel. visc. = 2.00 (m-cresol), Mn = 16500, Mw = 34000

** PET, rel. visc. = 1.60 (m-cresol), Mn = 20,000, Mw = 43,000

6

3. Process according to claim 1, characterized in that the functional groups are chosen from the group comprising amine, hydroxyl or thiol, (carboxylic) acid, acid anhydride, acid chloride, nitrile and imine groups.

5. 4. Process according to claim 1, characterized in that the melting point of the polymer is at least 180°C.

5. Process according to claim 4, characterized in that the melting point is at least 220°C.

6. Process according to claim 2, characterized in that the polymer is a polyamide or copolymer thereof.

10. 7. Process according to claim 6, characterized in that the polyamide is ε-polycaprolactam.

8. Process according to claim 3, characterized in that the functional groups are amine groups.

15. 9. Process according to claim 4, characterized in that the compound having at least 3 functional groups is a dendrimer compound.

10. Process according to claim 9, characterized in that the compound is an amine-terminated dendrimer compound or a salt thereof.

20. 11. Process according to claim 10, characterized in that the polymer having a hetero atom in the chain is a polyamide or a copolymer thereof.

12. Process according to claim 2, characterized in that the polymer is a polyester.

25. 13. Process according to claim 12, characterized in that the polyester is chosen from the group comprising polyethylene terephthalate, polybutylene terephthalate and polylactone.

14. Process according to claim 13, characterized in that the polylactone is poly-ε-caprolactone.

30. 15. Process according to claim 3, characterized in that the functional groups are hydroxyl groups.

16. Star-branched polymer obtained by the process according to claim 1.

35. 17. Star-branched polymer, the polymer being derived from an AABB polyamide or polyester which can be obtained through polycondensation of a di-acid with a diamine or diol, respectively.

40

45

50

55

DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
A	WO-A-92 08749 (CORNELL RESEARCH) ---		C08G81/00 C08G85/00 C08G69/48 C08G63/20 C08G73/02 C08G18/83
A	EP-A-0 504 108 (CIBA-GEIGY) ---		
A	WO-A-93 17060 (PERSTORP AB) ---		
A	WO-A-93 21259 (CORNELL RESEARCH) -----		

TECHNICAL FIELDS SEARCHED (Int.Cl.6)

C08G

The present search report has been drawn up for all claims

Place of search	Date of completion of the search	Examiner
THE HAGUE	10 May 1995	Leroy, A

CATEGORY OF CITED DOCUMENTS

X : particularly relevant if taken alone
Y : particularly relevant if combined with another document of the same category
A : technological background
O : non-written disclosure
P : intermediate document

T : theory or principle underlying the invention
E : earlier patent document, but published on, or after the filing date
D : document cited in the application
L : document cited for other reasons

& : member of the same patent family, corresponding document

EPO FORM 1503 03.82 (P04C01)